

IUPITAL® ACETAL COPOLYMER ENGINEERING THERMOPLASTIC

IUPITAL® IS A REGISTERED TRADEMARK OF MITSUBISHI ENGINEERING PLASTICS CORPORATION

IUPITAL® F20

IUPITAL® F20-01 / F20-02 / F20-03 are the standard medium viscosity (medium melt flow) grades in the Iupital® Polyacetal range and are suited to general purpose injection moulding applications. Offering an exceptional combination of processability, rigidity, frictional wear, heat and chemical resistance, typical applications include mechanical clips, lock linkages and automotive petrol caps.

Note: [No mould release = 01] / [Standard mould release = 02] / [Low mould deposit = 03].

Note: The letters "UV" or "W" indicate UV stabilisation has been added [ie: Iupital® F20-03-W].

| | CONDITIONS | UNITS | TYPICAL VALUES | TESTING METHODS |
|---|----------------------------|-------------------|-------------------|--------------------|
| <u>1. Mechanical Properties</u> | | | | |
| Notched Izod Impact Strength | 12.7 x 3.2 mm | J/m | 64 | ASTM D256 |
| Tensile Strength | 12.7 x 3.2 mm @ 20 mm/min | MPa | 61.3 | ASTM D638 |
| Elongation to Fail | 12.7 x 3.2 mm @ 20 mm/min | % | 60 | ASTM D638 |
| Flexural Strength | 12.7 x 6.4 mm @ 2.8 mm/min | MPa | 89.7 | ASTM D790 |
| Flexural Modulus | 12.7 x 6.4 mm @ 2.8 mm/min | MPa | 2600 | ASTM D790 |
| Shear Strength | 2.0 mm | MPa | 54.9 | ASTM D732 |
| Tensile Impact Strength | 1.6 mm | kJ/m ² | 120 | ASTM D1822 |
| <u>2. Thermal Properties</u> | | | | |
| Heat Deflection Temperature | 12.7 x 6.4 mm @ 1.82 MPa | °C | 110 | ASTM D648 |
| | 12.7 x 6.4 mm @ 0.46 MPa | °C | 158 | ASTM D648 |
| Melting Temperature | | °C | 165 | DSC |
| Coefficient of Linear Thermal Expansion | | cm/cm/°C | 13 exp-5 | ASTM D696 |
| <u>4. Physical Properties</u> | | | | |
| Melt Flow Rate | 190°C, 2.16 kg | g/10 min | 9.0 | ASTM D1238 |
| Specific Gravity | | - | 1.41 | ASTM D792 |
| Rockwell Hardness | | M | 80 | ASTM D785 |
| UL Flammability | 0.8 mm | Rating | HB | UL 94 |
| Water Absorption | 24 hours | % | 0.22 | ASTM D570 |
| Mould Shrinkage | 3.0 x Ø100 mm disc | % | 2.0±0.4 | ASTM D955 |
| <u>5. Electrical Properties</u> | | | | |
| Volume Resistivity | - | Ohm.cm | 1.0 exp +14 | - |

TYPICAL PROCESSING CONDITIONS

IUPITAL® F20

The following typical guidelines are offered as initial processing conditions for **IUPITAL® F20**. In practice, processing parameters may need to be varied to give commercially acceptable performance in conjunction with optimum physical properties. For specific technical advice on part design or processing conditions, contact the Marplex Technical Service Department.

| | |
|--|---------------------------------|
| Temperature of pellet bed in dehumidifying drier | 80 - 90 °C |
| Minimum drying time at desired pellet bed temp | 2 - 3 hours |
| Mould temperature | 50 - 90 °C |
| Nozzle temperature | Do not exceed stock temperature |
| Stock temperature | 190 - 210 °C |
| Cylinder temperatures | Rear 165 - 185 °C |
| | Middle 175 - 195 °C |
| | Front 185 - 205 °C |
| Fill speed | Medium - Fast |
| Screw speed | 40 - 60 rpm |
| Screw back pressure | 0.1 - 0.5 MPa |
| Injection pressure | 60 - 130 MPa |
| Clamp pressure | 3 - 5 kN/cm ² |

Comment(s):

- 1 Cleanliness of the dryer, machine hopper and machine screw/barrel/nozzle assembly are essential for processing Iupital® Polyacetal and producing contamination free moulded components.
- 2 Iupital® Polyacetal is not compatible during moulding with other polymers.
- 3 It is suggested that the pre-drying, moulding die and material temperatures are manually confirmed using a hand held temperature measuring device.

Conversions: 1 MPa = 145 psi
= 10.2 kg/cm²
= 10 bar
°C = 5(°F-32)/9
1 kN/cm² = 0.65 ton/in²

(+) 18816996168

Ponciplastics.com