

(+) 18816996168

Ponciplastics.com



**Product Data Sheet &
General Processing Conditions**

**RTP 2285 HF
Polyetheretherketone (PEEK)
Carbon Fiber
High Flow**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.41	1.41	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0005 in/in	0.05 %	D 955
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.4 ft-lbs/in	75 J/m	D 256
unnotched 1/8 in (3.2 mm) section	14.0 ft-lbs/in	747 J/m	D 4812
Tensile Strength	39000 psi	269 MPa	D 638
Tensile Elongation	1.4 %	1.4 %	D 638
Tensile Modulus	4.00 x 10 ⁶ psi	27580 MPa	D 638
Flexural Strength	55000 psi	379 MPa	D 790
Flexural Modulus	3.70 x 10 ⁶ psi	25512 MPa	D 790
ELECTRICAL			
Volume Resistivity	< 1E5 ohm.cm	< 1E5 ohm.cm	D 257
THERMAL			
Deflection Temperature @ 264 psi (1820 kPa)	600 °F	316 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801
Coefficient of Linear Thermal Expansion Flow Direction	0.1 x 10 ⁻⁵ /°F	0.2 x 10 ⁻⁵ /°C	E 831
Transverse Direction	2.5 x 10 ⁻⁵ /°F	4.5 x 10 ⁻⁵ /°C	E 831

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	12000 - 18000 psi	83 - 124 MPa
Melt Temperature	660 - 750 °F	349 - 399 °C
Mold Temperature	325 - 425 °F	163 - 218 °C
Drying	3 hrs @ 300 °F	3 hrs @ 149 °C
Moisture Content	0.10 %	0.10 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Desiccant Type Dryer Required.