

Technical Data Sheet

Diamond Abs 3501 ESCR


Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

General			
Features	• High ESCR (Stress Crack Resist.)		
Agency Ratings	• EC 1907/2006 (REACH)	• EU 2002/96/EC (WEEE)	
RoHS Compliance	• RoHS Compliant		
UL File Number	• E150937		
Forms	• Pellets		
Processing Method	• Extrusion		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.05	1.05 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹			ASTM D1238
200°c/5.0 Kg	0.70 g/10 min	0.70 g/10 min	
230°c/3.8 Kg	2.5 g/10 min	2.5 g/10 min	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield)	6500 psi	44.8 MPa	ASTM D638
Flexural Modulus - Tangent ³	340000 psi	2340 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°f (23°c), 0.125 In (3.18 Mm)	5.0 ft·lb/in	270 J/m	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	108	108	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed, 0.125 In (3.18 Mm)	171 °F	77.2 °C	
264 Psi (1.8 Mpa), Annealed, 0.125 In (3.18 Mm)	201 °F	93.9 °C	
Vicat Softening Temperature	219 °F	104 °C	ASTM D1525 ⁴
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94

Technical Data Sheet

Diamond Abs 3501 ESCR

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 to 185 °F	80 to 85 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Rear Temperature	374 to 482 °F	190 to 250 °C
Middle Temperature	374 to 482 °F	190 to 250 °C
Front Temperature	374 to 482 °F	190 to 250 °C
Mold Temperature	104 to 176 °F	40 to 80 °C
Injection Rate	Moderate-Fast	Moderate-Fast

Notes

- ¹ Procedure A
- ² 2.0 in/min (51 mm/min)
- ³ 0.050 in/min (1.3 mm/min)
- ⁴ Loading 1 (10 N)

Notes

These are typical property values not to be construed as specification limits.