

Technical Data Sheet

Diamond Abs 3501 GF-30

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• High Impact Resistance		
Agency Ratings	• EC 1907/2006 (REACH) • EU 2002/96/EC (WEEE)		
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.24	1.24 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹			ASTM D1238
200°C/5.0 Kg	0.10 g/10 min	0.10 g/10 min	
230°C/3.8 Kg	3.0 g/10 min	3.0 g/10 min	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield)	11400 psi	78.3 MPa	ASTM D638
Flexural Modulus ³	817000 psi	5630 MPa	ASTM D790B

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 In (3.18 Mm))	1.2 ft·lb/in	64 J/m	ASTM D256A

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Annealed, 0.125 In (3.18 Mm)	217 °F	103 °C	
Vicat Softening Temperature	239 °F	115 °C	ASTM D1525 ⁴

Technical Data Sheet

Diamond Abs 3501 GF-30

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 to 185 °F	80 to 85 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Rear Temperature	374 to 482 °F	190 to 250 °C
Middle Temperature	374 to 482 °F	190 to 250 °C
Front Temperature	374 to 482 °F	190 to 250 °C
Mold Temperature	104 to 176 °F	40 to 80 °C
Injection Rate	Moderate-Fast	Moderate-Fast

Notes

¹ Procedure A

² 2.0 in/min (51 mm/min)

³ 0.050 in/min (1.3 mm/min)

⁴ Loading 1 (10 N)

Notes

These are typical property values not to be construed as specification limits.