

Technical Data Sheet

Polyflam RABS 90000 UV5 WHI85985



Acrylonitrile Butadiene Styrene

Product Description

Flame retardant ABS standard grade without PBDE and higher thermal stability

Processing Method	Injection Molding
Attribute	Good Processability; Good Thermal Stability; Non Blooming
Additive	Flame Retardant
Resin ID	ABS FR17

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (220 °C/10.0 kg)	30	cm ³ /10 min	ISO 1133
Density, (Method A)	1.20	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	40.0	MPa	ISO 527-2
Tensile Strain at Yield, (Type 1A, 50 mm/min)	3.0	%	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	2200	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	10	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	5.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	80	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	45	kJ/m ²	ISO 179
Hardness			
Ball Indentation Hardness	113	MPa	ISO 2039-1
Ball Pressure Test, (90 °C)	Pass		IEC 60695-10-2
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	96.0	°C	ISO 306
(A (10N), 50 °C/h)	105	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	92.0	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	80.0	°C	ISO 75-2/A
RTI Elec			
(1.5 mm)	60.0	°C	UL 746B
(3.0 mm)	60.0	°C	UL 746B

RTI Imp			
(1.5 mm)	60.0	°C	UL 746B
(3.0 mm)	60.0	°C	UL 746B
RTI Str			
(1.5 mm)	60.0	°C	UL 746B
(3.0 mm)	60.0	°C	UL 746B
Electrical			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	475	V	IEC 60112
High Amp Arc Ignition			UL 746A
Surface Resistivity	>1.0E+15	ohm	IEC 60093
Flammable			
Hot-wire Ignition (HWI)			UL 746A
Burning Rate			
(2.00 mm, Self-Extinguishing)	0.0	mm/min	ISO 3795
(2.00 mm, Self-Extinguishing)	0.0	mm/min	FMVSS 302
Glow Wire Flammability Index			
(1.5 mm)	960	°C	IEC 60695-2-12
(3.0 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			
(1.5 mm)	725	°C	IEC 60695-2-13
(3.0 mm)	725	°C	IEC 60695-2-13
Oxygen Index	28	%	ISO 4589-2
UL Information			
Flame Rating			
(1.5 mm)	V-0		UL 94
(3.0 mm)	V-0		UL 94
Flammability Classification			
(1.5 mm)	V-0		IEC 60695-11-10, -20
(3.0 mm)	V-0		IEC 60695-11-10, -20
UL File Number	E86615		

Injection Parameters		Nominal Value	Units
Drying Time		2.0 to 4.0	hr
Drying Temperature		70 to 80	°C
Screw Speed		<300	mm/sec
Processing (Melt) Temp		220 to 240	°C
Injection Rate		Slow-Moderate	
Back Pressure		5.00 to 10.0	MPa
Mold Temperature		40 to 60	°C