

Technical Data Sheet

Polyman ABS K1836 I WHI80390



Acrylonitrile Butadiene Styrene

Product Description

Easy flow medium impact ABS grade

Processing Method Injection Molding

Attribute Good Flow; Medium Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (220 °C/10.0 kg)	35	cm ³ /10 min	ISO 1133
Density, (Method A)	1.10	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	42.0	MPa	ISO 527-2
Tensile Strain at Yield, (Type 1A, 50 mm/min)	2.2	%	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	2500	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	15	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched, (23 °C, Type 1, Edgewise)	No Break		ISO 179
Thermal			
Vicat Softening Temperature, (B (50N), 50 °C/h)	95.0	°C	ISO 306
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	77.0	°C	ISO 75-2/A
Flammable			
Burning Rate			
(2.00 mm)	<100	mm/min	FMVSS 302
(2.00 mm)	<100	mm/min	ISO 3795

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	230 to 250	°C
Mold Temperature	30 to 80	°C