

Technical Data Sheet

Ronfalin ABS 1411 M FC

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

Product Description

Good flowing ABS grade for self-colouring, for parts with matt surface finish

General

Processing Method • Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.04 g/cm³	1.04 g/cm³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 Kg)	8.0 cm³/10min	8.0 cm³/10min	ISO 1133
Water Absorption			ISO 62
Equilibrium, 73°F (23°C), 50% Rh	0.30 %	0.30 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	196000 psi	1350 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	3920 psi	27.0 MPa	ISO 527-2/1A/50
Nominal Tensile Strain at Break	100 %	100 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	4.3 ft·lb/in²	9.0 kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength			
-22°F (-30°C)	No Break	No Break	ISO 179
73°F (23°C)	No Break	No Break	ISO 179/1eU
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	97	97	ISO 2039-2
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature			
--	214 °F	101 °C	ISO 306/B50
--	223 °F	106 °C	ISO 306/A50
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94

Additional Information

1.) Not for use in medical or pharmaceutical applications

Notes

These are typical property values not to be construed as specification limits.