

Technical Data Sheet

Ronfalin ABS 1412 GF 17

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

Product Description

17% glass fiber reinforced ABS compound. (Former name: POLYMAN FABS 17GF)

General

Filler / Reinforcement	• Glass Fiber, 17% Filler by Weight
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.16 g/cm ³	1.16 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 Kg)	12 cm ³ /10min	12 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	783000 psi	5400 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	10600 psi	73.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	1.9 %	1.9 %	ISO 527-2/5
Flexural Modulus ¹	856000 psi	5900 MPa	ISO 178
Flexural Stress			ISO 178
2.2% Strain ¹	16200 psi	112 MPa	
2.3% Strain ^{2, 3}	14500 psi	100 MPa	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	2.9 ft·lb/in ²	6.0 kJ/m ²	
73°F (23°C)	3.3 ft·lb/in ²	7.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	10 ft·lb/in ²	22 kJ/m ²	
73°F (23°C)	10 ft·lb/in ²	22 kJ/m ²	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	19900 psi	137 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	216 °F	102 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	203 °F	95.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	216 °F	102 °C	ISO 306/B50
--	225 °F	107 °C	ISO 306/A50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index (Solution A)	600 V	600 V	IEC 60112

Technical Data Sheet

Ronfalin ABS 1412 GF 17

Acrylonitrile Butadiene Styrene

LyondellBasell Industries

Engineering Plastics

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1290 °F	700 °C	
0.12 In (3.0 Mm)	1290 °F	700 °C	

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

Ronfalin ABS 1412 GF 17

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	446 to 500 °F	230 to 260 °C
Mold Temperature	104 to 176 °F	40 to 80 °C

Notes

¹ 0.079 in/min (2.0 mm/min)

² 0.091 in/min (2.3 mm/min)

³ at Break

Notes

These are typical property values not to be construed as specification limits.