

Technical Data Sheet

Ronfalin ABS RXG03 NAT 0-0377



Acrylonitrile Butadiene Styrene

Product Description

Ronfalin RXG03 NATURAL 0-0377 is a Acrylonitrile Butadiene Styrene Glass Fiber, 20% filled material.

Application Camera Applications

Filler/Reinforcement Glass Fiber, 20%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (220 °C/10.0 kg)	8.0	g/10 min	ISO 1133
Density	1.2	g/cm ³	ISO 1183
Mechanical			
Flexural Modulus	3700	MPa	ISO 178
Impact			
Notched Izod Impact Strength, (Type 1, Notch A)	10	kJ/m ²	ISO 180
Hardness			
Ball Indentation Hardness	108	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature, (B (50N), 50 °C/h)	110	°C	ISO 306
Deflection Temperature Under Load Unannealed (1.80 MPa)	90	°C	ISO 75-2/A
Electrical			
Dielectric Strength	>35	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI), (Solution A)	>600	V	IEC 60112
Surface Resistivity	1E+16	ohm	IEC 60093
UL Information			
Flame Rating, (1.6 mm)	HB		UL 94