

Technical Data Sheet

SCHULAREC ABS 1012/01 - C

Acrylonitrile Butadiene Styrene

Product Description

Recycled medium impact ABS produced from Post Consumer sources (WEEE derived). ABS 1012/01 is suitable for injection moulding applications.

General

Processing Method	• Injection Molding
Resin ID (ISO 1043)	• ABS

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.05 g/cm ³	1.05 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	8.0 g/10 min	8.0 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Yield)	5800 psi	40.0 MPa	ISO 527-2/1A/50
Flexural Modulus	305000 psi	2100 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	4.8 ft·lb/in ²	10 kJ/m ²	ISO 179/1eA
Notched Izod Impact Strength	4.8 ft·lb/in ²	10 kJ/m ²	ISO 180
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	176 °F	80.0 °C	ISO 75-2/A
Vicat Softening Temperature	203 °F	95.0 °C	ISO 306/B50
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Notes

These are typical property values not to be construed as specification limits.