

Technical Data Sheet

Ronfalin ASA 3421 U WHI81840



Acrylonitrile Styrene Acrylate

Product Description

Impact modified ASA with increased heat resistance and very good UV stability. (Former name: POLYMAN ASA E/MI 1010 H UV+)

Processing Method Extrusion; Injection Molding

Attribute Good Flow; UV Stabilized

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (220 °C/10.0 kg)	7.0	cm ³ /10 min	ISO 1133
Density, (Method A)	1.06	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	50.0	MPa	ISO 527-2
Nominal Tensile Strain at Break, (50 mm/min, Type 1A)	5.0	%	ISO 527-2
Flexural Modulus, (2.0 mm/min)	2600	MPa	ISO 178
Tensile Strain at Yield, (Type 1A, 50 mm/min)	3.6	%	ISO 527-2
Tensile Stress at Break, (Type 1A, 50 mm/min)	45.0	MPa	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	2400	MPa	ISO 527-1
Flexural Stress, (2.0 mm/min, 4.8%)	80.0	MPa	ISO 178
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	12	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	2.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	60	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	26	kJ/m ²	ISO 179
Hardness			
Ball Indentation Hardness, (H 358/30)	96.0	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	102	°C	ISO 306
(A (10N), 50 °C/h)	118	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	103	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	88.0	°C	ISO 75-2/A
Electrical			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1

Comparative Tracking Index (CTI), (Solution A)	600	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093
Flammable			
Burning Rate			
(2.00 mm)	<100	mm/min	FMVSS 302
(2.00 mm)	<100	mm/min	ISO 3795
Glow Wire Ignition Temperature			
(1.5 mm)	700	°C	IEC 60695-2-13
(3.0 mm)	700	°C	IEC 60695-2-13
UL Information			
Flammability Classification			
(1.5 mm)	HB		IEC 60695-11-10, -20
(3.0 mm)	HB		IEC 60695-11-10, -20

Injection Parameters	Nominal	
	Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	240 to 270	°C
Mold Temperature	40 to 80	°C