

Technical Data Sheet

ICORENE® N1008

Ethylene Vinyl Acetate Copolymer
Custom Powders



Product Description

ICORENE® N1008 is a premium copolymer of ethylene vinyl acetate specifically designed for the preparation of masterbatch. The powder form can achieve better colour developments or additive dispersion in a masterbatch than the pellet form.

The vinyl acetate content is about 9%.


This grade has a maximum processing temperature of 270°C.

General

Additive	• Heat Stabilizer		
Features	• Copolymer • Dispersible	• Food Contact Acceptable • Good Colorability	• Heat Stabilized
Uses	• Masterbatch		
Agency Ratings	• EU Food Contact, Unspecified Rating	• FDA Food Contact, Unspecified Rating	
Forms	• Powder		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.929 g/cm³	0.929 g/cm³	Internal Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0 g/10 min	9.0 g/10 min	ASTM D1238
Vinyl Acetate Content	9.0 wt%	9.0 wt%	Internal Method
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	10700 psi	74.0 MPa	ASTM D638
Tensile Elongation (Break)	> 100 %	> 100 %	ASTM D638
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore A)	93	93	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	162 °F	72.0 °C	ASTM D1525
Peak Melting Temperature	205 °F	96.0 °C	ASTM D3418

Technical Data Sheet
ICORENE® N1008
Ethylene Vinyl Acetate Copolymer
Custom Powders



Injection	Nominal Value (English)	Nominal Value (SI)
Processing (Melt) Temp	< 518 °F	< 270 °C

Notes
These are typical property values not to be construed as specification limits.