

Technical Data Sheet

Alathon H5618

High Density Polyethylene

Product Description

Alathon H5618 provides easy processing characteristics and exhibits excellent toughness properties and color as well as low odor and good processing stability. Typical applications include housewares, containers, caps and closures.

Regulatory Status

For regulatory compliance information, see *Alathon* H5618 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Caps & Closures; Containers; Housewares
Market	Rigid Packaging
Processing Method	Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	18	g/10 min	18	g/10 min	ASTM D1238
Density, (23 °C)	0.956	g/cm ³	0.956	g/cm ³	ASTM D1505
Bulk Density	33-37	lb/ft ³	529-593	kg/m ³	ASTM D1895
Spiral Flow	11.7	in	29.7	cm	LYB Method
Mechanical					
Flexural Modulus					
(1% Secant)	204000	psi	1410	MPa	ASTM D790
(2% Secant)	171000	psi	1180	MPa	ASTM D790
Flexural Young's Modulus	217000	psi	1490	MPa	ASTM D790
Tensile Modulus, (1% Secant)	123000	psi	848	MPa	ASTM D638
Tensile Young's Modulus	153000	psi	1050	MPa	ASTM D638
Tensile Stress at Break, (23 °C)	3480	psi	24.0	MPa	ASTM D638
Tensile Stress at Yield, (23 °C)	4230	psi	29.2	MPa	ASTM D638
Tensile Elongation at Break, (23 °C)	62	%	62	%	ASTM D638
Tensile Elongation at Yield, (23 °C)	8	%	8	%	ASTM D638
Impact					
Notched Izod Impact Strength, (23 °C)	0.58	ft-lb/in	31	J/m	ASTM D256
Unnotched Impact Strength, (-18 °C)	No Break		No Break		ASTM D4812
Hardness					
Shore Hardness, (Shore D, max)	69		69		ASTM D2240
Thermal					
Vicat Softening Temperature	256	°F	125	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746

Deflection Temperature Under Load, (66 psi, Unannealed)	163 °F	73 °C	ASTM D648
Melting Temperature	266.4 °F	130.2 °C	ASTM D3418
Crystallization Temperature	239.7 °F	115.4 °C	ASTM D3418

Notes

Conditions of Tensile Stress and Elongation values are: 50 mm/min, Type IV specimen.

Conditions of Flexural Modulus values are: 0.5 inches/min or 12.5 mm/min.

Conditions of Tensile Modulus values are: 50 mm/min, Type I Specimen.

Spiral Flow measures the number of inches of flow produced when molten resin is injected into a long, spiral channel (0.0625" insert), at a constant injection pressure of 1000 psi with a melt temperature of 440 °F.

Deflection Temperature Under Load and Low Temperature Brittleness data are for control and development work and are not intended for use in design or predicting performance at elevated or sub-ambient temperatures.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.