

Alathon

# L5840

High Density Polyethylene

Blow Molding Grade

Melt Index 0.35 Density 0.958



## Applications

Alathon L5840 is a lightweighting resin that exhibits excellent color, low odor and provides processing stability. Typical applications include household chemicals, industrial chemicals, detergent and motor oil bottles. L5840 containing antistat is available as L5840AS.

## Regulatory Status

L5840 meets the requirements of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food..." Specific limitations or conditions of use may apply. Contact your Equistar product safety representative for more information.

## Processing Techniques

Specific recommendations for processing L5840 can only be made when the processing conditions, equipment and end use are known.

## Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.35	g/10 min	D1238
Density	0.958	g/cm <sup>3</sup>	D1505
Tensile Strength @ Yield	4,400	psi	D638
Elongation @ Break	>600	%	D638
Flexural Modulus	211,000	psi	D790
Tensile Impact	140	ft-lb/in.	D1822
Low Temperature Brittleness, F <sub>50</sub>	<-76	°C	D746
Heat Deflection Temperature @ 66 psi	81	°C	D648
Vicat Softening Point	128	°C	D1525
Hardness, Shore D	68		D2240
Environmental Stress Crack Resistance, F <sub>50</sub>	25	hrs	D1693 <sup>1</sup>

<sup>1</sup> 100% Igepal® CO-630, 50°C

® Igepal is a registered trademark of Rhône-Poulenc Co., Inc.

These are typical values not to be construed as specification limits.