(+) 188 1699 6168 hongrunplastics.com

Technical Data Sheet

Hostalen GM 5010 T3 S YELLOW

High Density Polyethylene



Hostalen GM 5010 T3 S yellow is a high density polyethylene (HDPE), yellow colored similar RAL 1018 with light stabilizer and high melt viscosity for identification marking stripes for gas pipes made from Hostalen GM 5010 T3 black.

Regulatory Status

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Status Commercial: Active

Availability Africa-Middle East; Asia-Pacific; Europe; South & Central America

Application Gas Pipe
Market Pipe

Processing Method Pipe; Sheet

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/5.0 kg)	0.45	g/10 min	ISO 1133-1
Density	0.972	g/cm³	ISO 1183-1
Thermal			
Oxidation Induction Time, (210 °C)	>=20	min	ISO 11357-6

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

Recommended melt temperatures: 190 °C to 230 °C.

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

