

LyondellBasell Microthene® MP655662 High Density Polyethylene (Unverified Data**)

Categories: [Polymer](#); [Thermoplastic](#); [Polyethylene \(PE\)](#); [High Density \(HDPE\)](#); [High Density Polyethylene \(HDPE\)](#); [Rotational Molding Grade](#)

Material Notes: Applications
 MICROTHENE MP 655-662 is a rotational molding powder that produces items with very smooth inner surface under a wide range of processing conditions. MP 655-662 can be used to make a variety of rotomolded items including light globes, storage containers, traffic crash barriers, ducting and equipment housings. This resin is also available in pellet form as PETROTHENE® GA 655-662.


Processing Techniques
 Specific recommendations for processing MP 655-662 can be made only when the required properties, processing equipment and end use are known.

Physical Properties
 MP 655-662 exhibits excellent impact strength at both room temperature and -40°F. It also has good warp resistance and stiffness.

This product is from the former Equistar product line.

Vendors: No vendors are listed for this material. Please [click here](#) if you are a supplier and would like information on how to add your listing to this material.

Physical Properties	Metric	English	Comments
Density	0.945 g/cc	0.0341 lb/in ³	Compression molded; ASTM D155
ESCR 100% Igepal®	30 hour @Thickness 3.17 mm	30 hour @Thickness 0.125 in	Cond. A, CO-630, Rotomolded, F ₅₀ ; ASTM D1693
ESCR 10% Igepal®	10 hour @Thickness 3.17 mm	10 hour @Thickness 0.125 in	Cond. A, CO-630, Rotomolded, F ₅₀ ; ASTM D1693
Melt Flow	5.0 g/10 min	5.0 g/10 min	Pellets; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	20.7 MPa	3000 psi	2"/min, Rotomolded; ASTM D638
Flexural Modulus	0.931 GPa @Thickness 3.17 mm	135 ksi @Thickness 0.125 in	1% Secant Modulus, Rotomolded; ASTM D790
Impact Test 	54.2 J @Thickness 3.17 mm, Temperature -40.0 °C	40.0 ft-lb @Thickness 0.125 in, Temperature -40.0 °F	Rotomolded; ARM STD
	136 J @Thickness 6.35 mm, Temperature -40.0 °C	100 ft-lb @Thickness 0.250 in, Temperature -40.0 °F	Rotomolded; ARM STD

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	66.0 °C @Thickness 3.17 mm	151 °F @Thickness 0.125 in	Rotomolded; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	42.0 °C @Thickness 3.17 mm	108 °F @Thickness 0.125 in	Rotomolded; ASTM D648

** This data sheet is not an active part of MatWeb and the information on it should not be considered reliable.

Inactive data sheets have usually been replaced with newer information on the same material. If this is the case, you can find the active data sheet by using any of our search tools, including the Quick Search box in the upper part of this page.

If you are unable to locate an active data sheet for this material, then this material is likely discontinued, although various other reasons may be behind its removal. In any event, do not rely on the information on this page to be accurate or maintained.

You may have reached this data sheet through an outdated bookmark or link. Please update your bookmark accordingly. We apologize if you have accessed this page through MatWeb's usual search tools.

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error. We also ask that you refer to MatWeb's [terms of use](#) regarding this information. [Click here](#) to view all the property values for this datasheet as they were originally entered into MatWeb.