(+) 188 1699 6168 hongrunplastics.com

Microthene F FA70000 lyondellbasell

ASTM D2240

High Density Polyethylene Microfine Polyolefin Powder Melt Index: 10 Density: 0.952

General Description	<i>Microthene</i> F polyolefin powders particles with narrow size distrib specialty applications. <i>Microthe</i> properties of a polyolefin resin w	ution suitable for use in ne F powders combine	h a broad range of the unique	
Regulatory Status	FA70000 meets the requirements of the Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer " in articles or components of articles intended for use in contact with food" Specific limitations or conditions of use may apply. Contact your Equistar product safety representative for more information.			
Processing Techniques	The microfine size and spherical shape of <i>Microthene</i> F powders facilitate dispersion in aqueous or organic systems. Specific suggestions can be made only when equipment, materials, process parameters and conditions of use are known.			
Typical				
Properties	Polymer Property	Nominal Value	Units	Test Method
	Melt Index	10	g/10 min	ASTM D1238
	Density	0.952	g/cc	ASTM D1505
	Vicat Softening Point	125.0 / 257.0	°C / °F	ASTM D1525
	Peak Melting Point	134.0 / 273.2	°C / °F	ASTM D3418
	Low Temperature Brittleness	-76.0 / -104.8	°C / °F	ASTM D746
	Tensile Strength @ Break	11.7 / 1,700	MPa/psi	ASTM D638
	Elongation @ Break	400	%	ASTM D638
	Flexural Modulus	1,103 / 160,000	MPa/psi	ASTM D790

66

Hardness, Shore D **Powder Property** Particle Shape Spherical Average Particle Size ETM Malvern* 20 micron 5 - 50 Particle Size Distribution micron **ETM Malvern*** Maximum Moisture Content 0.1 % ETM 156*

* ETM = Equistar Test Method

These are typical values not to be construed as specification limits.