

Technical Data Sheet
POLYAXIS® RLLP 622
High Density Polyethylene
Rotomolding



General			
Appearance	• Colors Available	• White	
Forms	• Pellets	• Powder	
Processing Method	• Rotational Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity ¹	1.02	1.02 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.5 g/10 min	6.5 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield, Rotational Molded)	2200 psi	15.2 MPa	ASTM D638
Tensile Elongation ² Break, Rotational Molded	50 %	50 %	ASTM D638
Flexural Modulus - 1% Secant (Rotational Molded)	85000 psi	586 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Impact Strength			ARM
-40°F (-40°C), 0.125 in (3.18 mm), Rotational Molded	20 ft·lb	27 J	
-40°F (-40°C), 0.250 in (6.35 mm), Rotational Molded ³	20 ft·lb	27 J	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed, Rotational Molded	118 °F	48.0 °C	
264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm), Rotational Molded	103 °F	39.2 °C	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm), Any Color)	V-2	V-2	UL 94

Notes

¹ Compression Molded

² 2.0 in/min (51 mm/min)

³ Dart weight 20 lbs

Notes

These are typical property values not to be construed as specification limits.