

## Technical Data Sheet

### *Petrothene* LB501031



High Density Polyethylene

#### Product Description

*Petrothene* LB501031 is selected by customers for its balance of good physical properties with excellent processability in blow molding applications.

<b>Application</b>	Furniture; General Sheet Extrusion; Sports, Leisure & Toys
<b>Market</b>	Outdoor Equipment
<b>Processing Method</b>	Extrusion Blow Molding; Sheet

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/21.6 kg)	11.5	g/10 min	11.5	g/10 min	ASTM D1238
Density, (23 °C)	0.949	g/cm <sup>3</sup>	0.949	g/cm <sup>3</sup>	ASTM D1505
<b>Mechanical</b>					
Flexural Modulus, (1% Secant)	168000	psi	1160	MPa	ASTM D790
Tensile Strength at Break	4900	psi	33.8	MPa	ASTM D638
Tensile Strength at Yield	3650	psi	25.2	MPa	ASTM D638
Tensile Elongation at Yield	1300	%	1300	%	ASTM D638
<b>Impact</b>					
Tensile Impact Strength	249	ft-lb/in <sup>2</sup>	523	kJ/m <sup>2</sup>	ASTM D1822
<b>Hardness</b>					
Shore Hardness, (Shore D)	68		68		ASTM D2240
<b>Thermal</b>					
Vicat Softening Temperature	259	°F	126	°C	ASTM D1525
Low Temperature Brittleness, F <sub>50</sub>	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	145	°F	63	°C	ASTM D648

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.