(+) 188 1699 6168 hongrunplastics.com

Petrothene

Typical Properties

LR734011

lyondellbasell

High Density Polyethylene Blow Molding Grade Melt Index 0.38 Density 0.953

Applications *Petrothene* LR734011 is a high density polyethylene resin that exhibits good stiffness and environmental stress crack resistance. Typical applications include bottles for household chemicals. This product contains synthetic antistat.

Regulatory<br/>StatusPetrothene LR734011 meets the requirements of the Food and Drug Administration regulation<br/>21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or<br/>components of articles intended for use in contact with food..." Specific limitations or conditions<br/>of use may apply. Contact your Equistar product safety representative for more information.

ProcessingSpecific recommendations for processing LR734011 can only be made when the processing<br/>conditions, equipment and end use are known.

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.38	a/10 min	D1238
Density	0.953	g/cc	D1505
Tensile Strength @ Yield	4,000	psi	D638
Elongation @ Break	>500	%	D638
Flexural Modulus	176,000	psi	D790
Tensile Impact	131	ft-lb/in.	D1822
Low Temperature Brittleness, F <sub>50</sub>	<-76	°C	D746
Heat Deflection Temperature @ 66 psi	75	°C	D648
Vicat Softening Point	127	°C	D1525
Hardness, Shore D	67		D2240
Environmental Stress Crack Resistance, F <sub>50</sub>	25	hrs	D1693 <sup>1</sup>
	>500	hrs	D2561

<sup>1</sup> 100% Igepal® CO-630, 50°C.

<sup>®</sup> Igepal is a registered trademark of Rhône-Poulenc Co., Inc.

These are typical values not to be construed as specification limits.

See page 2 for additional information.