

Technical Data Sheet

Lupolen 1840D

Low Density Polyethylene



Product Description

Lupolen 1840 D is a non-additivated, low density polyethylene. It is characterized by a high melt strength leading to a good bubble stability during blown film extrusion. It is delivered in pellet form.

This product is not intended for use in medical and pharmaceutical applications.

Regulatory Status

For regulatory compliance information, see *Lupolen 1840D* [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Europe
Application	Agriculture Film; Bags & Pouches; Heavy Duty Packaging; Liner Film; Shrink Film; Stretch Hood
Market	Flexible Packaging
Processing Method	Blown Film
Attribute	General Purpose; Good Processability; Good Tear Strength; Good Toughness

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	0.25	g/10 min	ISO 1133-1
Density	0.919	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	200	MPa	ISO 527-1, -2
Tensile Stress at Yield	9	MPa	ISO 527-1, -2
Film			
Dart Drop Impact Strength, F50	280	g	ASTM D1709
Tensile Strength			
MD	27	MPa	ISO 527-1, -3
TD	25	MPa	ISO 527-1, -3
Tensile Strain at Break			
MD	200	%	ISO 527-1, -3
TD	500	%	ISO 527-1, -3
Coefficient of Friction	>0.8		ISO 8295
Impact			
Failure Energy	6.5	J/mm	DIN 53373
Film thickness: 70 µm			
Thermal			
Vicat Softening Temperature, (A/50 N)	93	°C	ISO 306
Peak Melting Point	108	°C	ISO 11357-3
Optical			
Haze, (50 µm)	<15	%	ASTM D1003

Gloss		
(20°)	>10	ASTM D2457
(60°)	>50	ASTM D2457
Additional Information		
Test Specimen	Film	
Film properties tested using 50 µm thickness blown film extruded at a melt temperature of 180°C and a blow-up ratio of 2.5:1.		
Processing Parameters		
Extrusion Temperature	170-220 °C	

Notes

These are typical property values not to be construed as specification limits.