

Lupolen 2421 H

Polyethylene, Low Density

Product Description

 $\it Lupolen~2421~H~is~an~additivated, low~density~polyethylene.~It~contains~an~antioxidant~and~is~delivered~in~pellet~form.$

Foodlaw compliance information about this product can be found in separate product documentation.

This product is not intended for use in medical and pharmaceutical applications.

Product Characteristics

Status Commercial: Active

Test Method used ISC

Availability Europe, Asia-Pacific, Africa-Middle East

Processing Methods Blown Film, Cast Film

Features Good Heat Seal, Opticals, Good Processability

Typical Customer Applications Bags & Pouches, Blown Film, Cast Film, Film, Shrink Film

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.924	g/cm³
Melt flow rate (MFR) (190°C/2.16kg)	ISO 1133	1.9	g/10 min
Mechanical			
Dart drop impact (50µm, Blown Film)	ASTM D 1709	110	g
Tensile Modulus	ISO 527-1, -2	260	MPa
Tensile Stress at Yield	ISO 527-1, -2	11.0	MPa
Tensile Strength	ISO 527-1, -3		
		25.0	MPa
Note: MD			
		21.0	MPa
Note: TD			
Tensile Strain at Break	ISO 527-1, -3		
		250	%
Note: MD			
Notes TD		600	%
Note: TD Thermal			
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	94.0	°C
Melting Temperature	ISO 3146	111	°C
Optical			
Haze (50µm)	ASTM D 1003	<8	%
Gloss	ASTM D 2457		
(20°, 50µm)		>50	
(60°, 50μm)		>100	
Film			
Melt Temperature		160 to 200	°C

Additional Properties

Film properties tested using 50 μ m thickness blown film extruded at a melt temperature of 180°C and a blow-up ratio of 1:2.5. Failure Energy, DIN 53373, 50 μ m: 4 J/mm

Failure Energy, DIN 53373, 50µm: 4 J/mm Coefficient of Friction, ISO 8295: >80% Recommended Thickness: 20 to 100 µm.

Note

Typical properties; not to be construed as specifications.