(+) 188 1699 6168 hongrunplastics.com



Lupolen 3010 D

Polyethylene, Low Density

Product Description

Lupolen 3010 D is a non-additivated, low density polyethylene. It is delivered in pellet form.

Foodlaw compliance information about this product can be found in separate product documentation.

This product is not intended for use in medical and pharmaceutical applications.

Product Characteristics

Status Commercial: Active

Test Method used ISO

Availability Europe

Processing Methods Blown Film, Extrusion Blow Molding

Features Opticals, Good Processability, Good Stiffness, Good

Toughness

Typical Customer Applications Bags & Pouches, Blown Film, Film, Food Packaging Film,

Shrink Film, Surface Protection Film

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.927	g/cm³
Melt flow rate (MFR) (190°C/2.16kg)	ISO 1133	0.25	g/10 min
Mechanical			
Dart drop impact (50µm, Blown Film)	ASTM D 1709	180	g
Tensile Modulus	ISO 527-1, -2	300	MPa
Tensile Stress at Yield	ISO 527-1, -2	13.0	MPa
Tensile Strength	ISO 527-1, -3		
		30.0	MPa
Note: MD			
		27.0	MPa
Note: TD			
Tensile Strain at Break	ISO 527-1, -3		
		250	%
Note: MD			0.4
Note: TD		600	%
Note: TD			
Thermal			
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	102	°C
Melting Temperature	ISO 3146	114	°C
Optical			
Haze (50µm)	ASTM D 1003	<7	%
Gloss	ASTM D 2457		
(20°, 50μm)		>35	
(60°, 50μm)		>90	

(+) 188 1699 6168 hongrunplastics.com

Film

Melt Temperature 170 to 220 °C

Additional Properties

Film properties tested using 50 μm thickness blown film extruded at a melt temperature of 200°C and a blow-up ratio of 1:2.5.

ESCR, Elenac: 15 hr

Failure Energy, DIN 53373, 70 $\mu m:$ 5 J/mm Coefficient of Friction, ISO 8295: >70% Recommended Film Thickness: 60 to 220 μm

Notes

Typical properties; not to be construed as specifications.