

# Lupolen 3020 K

### Polyethylene, Low Density

#### **Product Description**

Lupolen 3020 K is a non-additivated, low density polyethylene with high rigidity, good opticals and good chemical resistance. It is delivered in pellet form.

Foodlaw compliance information about this product can be found in separate product documentation.

This product is not intended for use in medical and pharmaceutical applications.

### **Product Characteristics**

Status Commercial: Active

Test Method used ISO

Availability Europe

Processing Methods Blown Film, Cast Film, Injection Molding

Features Good Heat Seal, Opticals, Good Processability, Good

Stiffness

**Typical Customer Applications**Blown Film, Cast Film, Film, Food Packaging Film, Lamination Film, Shrink Film, Surface Protection Film

**Typical Properties** Method Value **Physical** Density ISO 1183 0.928 g/cm<sup>3</sup> Melt flow rate (MFR) (190°C/2.16kg) ISO 1133 4.0 g/10 min Mechanical ASTM D 1709 90 Dart drop impact (50µm, Blown Film) g 300 Tensile Modulus ISO 527-1, -2 MPa Tensile Stress at Yield ISO 527-1, -2 13.0 MPa Tensile Strength ISO 527-1, -3 20.0 MPa Note: MD 17.0 MPa Note: TD Tensile Strain at Break ISO 527-1, -3 350 % Note: MD 600 % Note: TD **Thermal** Vicat softening temperature (A50 (50°C/h 10N)) ISO 306 97.0 °C Melting Temperature ISO 3146 °C 114 Optical Haze (50µm) **ASTM D 1003** <7 % Gloss **ASTM D 2457** (20°, 50µm) >80 (60°, 50µm) >115 Film Melt Temperature 150 to 190 °C

## **Additional Properties**

Film properties tested using 50  $\mu m$  thickness blown film extruded at a melt temperature of 170°C and a blow-up ratio of 1:2.5.

Failure Energy, DIN 53373, 50 µm: 3.5 J/mm Coefficient of Friction, ISO 8295: >80% Recommended Film Thickness: 15 to 40 µm

### Notes

Typical properties; not to be construed as specifications.