

Technical Data Sheet

Microthene MN70100



Low Density Polyethylene

Product Description

Microthene G polyolefin powders are ground, irregularly-shaped particles for use in a broad range of specialty applications. *Microthene* G powders combine the unique properties of a polyolefin resin with a small ground particle size.

Application	Automotive Parts; Colour Concentrates; Industrial; Interior Automotive Applications; Structural Parts
Market	Consumer Products; Flexible Packaging; Healthcare; Industrial, Building & Construction
Processing Method	Powders

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	70	g/10 min	70	g/10 min	ASTM D1238
Density, (23 °C)	0.912	g/cm ³	0.912	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus	27000	psi	186	MPa	ASTM D790
Tensile Strength at Break	1100	psi	7.7	MPa	ASTM D638
Tensile Elongation at Break	400	%	400	%	ASTM D638
Hardness					
Shore Hardness					
(Shore D, max)	51		51		ASTM D2240
(Shore D, 15 sec)	44		44		ASTM D2240
Thermal					
Vicat Softening Point	168.1	°F	75.6	°C	ASTM D1525
Low Temperature Brittleness	-8.9	°F	-22.7	°C	ASTM D746
Additional Information					
Particle Shape	Irregular		Irregular		LYB Method
Average Particle Size	35	mesh	35	mesh	LYB Method