(+) 188 1699 6168 hongrunplastics.com

Microthene G

lyondellbasell

Low Density Polyethylene Ground Polyolefin Powder Melt Index: 3.7 Density: 0.923

General Description	<i>Microthene</i> G polyolefin powders are ground, irregularly-shaped particles for use in a broad range of specialty applications. <i>Microthene</i> G powders combine the unique properties of a polyolefin resin with a small ground particle size.			
Regulatory Status	MN72200 meets the requirements of the Food and Drug Administration, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "articles or components of articles intended for use in contact with food" Specific limitations or conditions of use may apply. Contact your Equistar product safety representative for more information.			
Processing Techniques	The small size and irregular shape of <i>Microthene</i> G powders facilitate dispersion with other components. Specific suggestions can be made only when equipment, materials, process parameters and conditions of use are known.			
Typical Properties	Polymer Property Melt Index Density Vicat Softening Point Peak Melting Point Low Temperature Brittleness Tensile Strength @ Break Elongation @ Break Flexural Modulus Hardness, Shore D Powder Property Particle Shape Average Particle Size	Nominal Value 3.7 0.923 94.6 / 202.3 109.0 / 228.2 -68.1 / -90.6 11.8 / 1,720 610 330 / 47,800 56 / 50 Irregular 50	Units g/10 min g/cc °C/°F °C/°F °C/°F MPa/psi % MPa/psi max / 15 sec mesh	Test Method ASTM D1238 ASTM D1505 ASTM D1525 ASTM D3418 ASTM D746 ASTM D638 ASTM D638 ASTM D638 ASTM D790 ASTM D2240

* ETM = Equistar Test Method

These are typical values not to be construed as specification limits.