

Technical Data Sheet

Network Polymers Ldpe 10 2523

Low Density Polyethylene
LyondellBasell Industries
Engineering Plastics

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.923 g/cm ³	0.923 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) ¹ (190°C/2.16 Kg)	24 g/10 min	24 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Break)	1600 psi	11.0 MPa	ASTM D638
Tensile Elongation (Break)	150 %	150 %	ASTM D638
Flexural Modulus ²	44000 psi	303 MPa	ASTM D790B
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature	< -31.0 °F	< -35.0 °C	ASTM D746

Notes

¹ Procedure A

² Method I (3 point load), 0.050 in/min (1.3 mm/min)

Notes

These are typical property values not to be construed as specification limits.