



Purell PE 3020 K

Polyethylene, Low Density

Product Description

Purell PE 3020 K is a non-additivated, low density polyethylene with high rigidity, good opticals and good chemical resistance. It is delivered in pellet form.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	Europe
Processing Methods	Blown Film, Cast Film, Injection Molding
Features	Good Heat Seal, Opticals, Good Processability, Good Stiffness
Typical Customer Applications	Healthcare Applications, Medical, Medical Devices, Medical Film, Pharmaceutical

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.928	g/cm ³
Melt flow rate (MFR) (190°C/2.16kg)	ISO 1133	4.0	g/10 min
Mechanical			
Dart drop impact (50µm, Blown Film)	ASTM D 1709	90	g
Tensile Modulus	ISO 527-1, -2	300	MPa
Tensile Stress at Yield	ISO 527-1, -2	13.0	MPa
Tensile Strength	ISO 527-1, -3	20.0	MPa
Note: MD		17.0	MPa
Note: TD			
Tensile Strain at Break	ISO 527-1, -3	350	%
Note: MD		600	%
Note: TD			
Thermal			
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	97.0	°C
Melting Temperature	ISO 3146	114	°C
Optical			
Haze (50µm)	ASTM D 1003	<7	%
Gloss	ASTM D 2457		
(20°, 50µm)		>80	
(60°, 50µm)		>115	
Film			
Melt Temperature		150 to 190	°C

Additional Properties

Film properties tested using 50 µm thickness blown film extruded at a melt temperature of 170°C and a blow-up ratio of 1:2.5.

Failure Energy, DIN 53373, 50 µm: 3.5 J/mm

Coefficient of Friction, ISO 8295: >80%

Recommended Film Thickness: 15 to 40 µm

Notes

Typical properties; not to be construed as specifications.