

Technical Data Sheet

Petrothene GA564189



Linear Low Density Polyethylene

Product Description

Petrothene GA564189 exhibits good stiffness and low temperature toughness. Typical applications include trash cans, industrial containers, housewares and toys.

Application	Housewares; Outdoor and Power Tools; Sports, Leisure & Toys; Trash Cans; Wire & Cable
Market	Compounding; Rigid Packaging; Wire & Cable
Processing Method	Compounding; Injection Molding; Wire & Cable

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	20	g/10 min	20	g/10 min	ASTM D1238
Density, (23 °C)	0.924	g/cm ³	0.924	g/cm ³	ASTM D1505
Spiral Flow	12.6	in	32.1	cm	LYB Method
Mechanical					
Flexural Modulus					
(1% Secant)	63000	psi	440	MPa	ASTM D790
(2% Secant)	55000	psi	380	MPa	ASTM D790
Tensile Strength at Break, (23 °C)	1200	psi	8	MPa	ASTM D638
Tensile Strength at Yield, (23 °C)	2100	psi	14	MPa	ASTM D638
Tensile Elongation at Yield, (23 °C)	12	%	12	%	ASTM D638
Hardness					
Shore Hardness, (Shore D)	57		57		ASTM D2240
Thermal					
Vicat Softening Temperature	196	°F	91	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	113	°F	45	°C	ASTM D648