(+) 188 1699 6168 hongrunplastics.com

Plexar

## PX3227

## lyondellbasell

Extrudable Tie Layer Resin Anhydride-Modified LLDPE

Melt Index 1.7 Density 0.913 General Plexar tie-layers are chemically modified re

General Description Plexar tie-layers are chemically modified resins used to bond unlike materials, primarily in packaging and industrial applications. Common adherents include polyethylene resins and copolymers, EVA, EMA, polypropylene, polyamide (nylon), ethylene vinyl alcohol copolymers (EVOH), ionomer and other sealants, polyethylene terephthalate (PET) resins and copolymers, styrenic polymers, metal, and paperboard. Product grades primarily used for blown and cast films, sheet and thermoforming, blow molding, extrusion coating and lamination, tubing, pipe, and other specialty applications are available in pellet form. Contact your *Plexar* sales and/or Equistar technical service representative for more information and specific recommendations for your application(s).

Regulatory Status PX3227 meets the requirements for the United States Food and Drug Administration regulation 21CFR 175.105 for adhesives. For more information, please contact your Equistar product safety representative.

Processing Techniques

A process melt temperature above 410°F (210°C) is recommended to ensure adhesion between adherents. More specific suggestions can be made only when equipment, process parameters and conditions of use are known.

		Nominal		ASTM
Typical	Property	Value	Units	Test Method
Properties	Melt Index	1.7	g/10 min	D1238
	Density	0.913	g/cc	D1505
	Vicat Softening Point	82	Õ	D1525
	Blown Film	2.0 mil gauge: 2:1 BUR		
	Notched Elmendorf Tear, MD (TD)	270 (590)	g	D1922
	Tensile Strength @ Yield, MD (TD)	8.8 (9.7)	MPa	D882
	Tensile Strength @ Break, MD (TD)	28.7 (22.1)	MPa	D882
	Elongation @ Yield, MD (TD)	30 (12)	%	D882
	Elongation @ Break, MD (TD)	840 (840)	%	D882
	WVTR	5.6	g/m²/day	F372*
	* @ 100% Humidity			
	Typical Properties; not to be construed as specifications.			