

Plexar

PX3610

Extrudable Tie Layer Resin

Anhydride-Modified LLDPE

Melt Index 2.1 Density 0.918



General Description

Plexar tie-layers are chemically modified resins used to bond unlike materials, primarily in packaging and industrial applications. Common adherents include polyethylene resins and copolymers, EVA, EMA, polypropylene, polyamide (nylon), ethylene vinyl alcohol copolymers (EVOH), ionomer and other sealants, polyethylene terephthalate (PET) resins and copolymers, styrenic polymers, metal, and paperboard. Product grades primarily used for blown and cast films, sheet and thermoforming, blow molding, extrusion coating and lamination, tubing, pipe, and other specialty applications are available in pellet form. Contact your *Plexar* sales and/or Equistar technical service representative for more information and specific recommendations for your application(s).

Regulatory Status

PX3610 meets the requirements for the United States Food and Drug Administration regulation 21CFR 175.105 for adhesives. For more information, please contact your Equistar product safety representative.

Processing Techniques

A process melt temperature above 410°F (210°C) is recommended to ensure adhesion between adherents. More specific suggestions can be made only when equipment, process parameters and conditions of use are known.

Typical Properties

| Property | Nominal Value | Units | ASTM Test Method |
|-----------------------|---------------|----------|------------------|
| Melt Index (190/2.16) | 2.1 | g/10 min | D1238 |
| Density | 0.918 | g/cc | D1505 |
| Vicat Softening Point | 99 | °C | D1525 |

Typical Properties; not to be construed as specifications.