(+) 188 1699 6168 hongrunplastics.com

## **Technical Data Sheet**

## Icorene 3940-6A042G HandicapBlue

Polyethylene, Linear Medium Density



## **Product Description**

*Icorene* 3940 is a linear medium density polyethylene developed for rotational molding applications. The resin is fully UV stabilized and suitable for general purpose applications. It has a good balance of properties such as toughness and stiffness.

Processing Method Rotomolding

Attribute Ablation Resistant; Good Processability; Good Stiffness; Good Toughness; UV

Resistant

Forms Pellets; Powder

Appearance Black; Colors Available; Natural Color

Additive UV Stabilizer

**Application** Containers; General Purpose; Outdoor Applications; Pallets; Tanks

|  | Nominal           |          |             |
|--|-------------------|----------|-------------|
| Typical Properties                                     | Value             | Units    | Test Method |
| Physical   |                   |          |             |
| Melt Flow Rate, (190 °C/2.16 kg)                       | 3.4 to 4.0        | g/10 min | ASTM D1238  |
| Density  | 0.939 to<br>0.941 | g/cm³    | ASTM D1505  |
| Mechanical   |                   |          |             |
| Tensile Strength at Yield, (50 mm/min)                 | 20.0              | MPa      | ASTM D638   |
| Environmental Stress Crack Resistance                  |                   |          |             |
| (10% Igepal)   | 50.0              | hr       | ASTM D1693  |
| (100% Igepal)  | >1000             | hr       | ASTM D1693  |
| Flexural Modulus, (1.3 mm/min)                         | 834               | MPa      | ASTM D790   |
| Impact   |                   |          |             |
| Impact Strength  |                   |          |             |
| (-40 °C, 3.18 mm, Rotational Molded)                   | 77                | J        | ARM         |
| (-40 °C, 6.35 mm, Rotational Molded)                   | >258              | J        | ARM         |
| Thermal  |                   |          |             |
| Deflection Temperature Under Load Unannealed (264 psi) | 40.6              | °C       | ASTM D648   |
| Deflection Temperature Under Load Unannealed (66 psi)  | 62                | °C       | ASTM D648   |
|  |                   |          |             |