

Technical Data Sheet

Alcryn 1060BK EXT BLK



Melt Processable Rubber

Product Description

Alcryn 1060BK EXT BLK is a Melt Processable Rubber material and is typically used in Blow Molding, Calendering, Extrusion, Vacuum Forming applications. Features include: Fast Molding Cycle, Good Weather Resistance, High Heat Resistance, Noise Damping, Oil Resistant, Ozone Resistant, Recyclable Material, and Vibration Damping.

Processing Method	Blow Molding; Calendering; Extrusion; Vacuum Forming
Attribute	Fast Molding Cycle; Good Weather Resistance; High Heat Resistance; Noise Damping; Oil Resistant; Ozone Resistant; Recyclable Material; Vibration Damping
Forms	Pellets
Appearance	Black
Application	Cable Jacketing; Coating Applications; Fabric Coatings; Flexible Grips; Gaskets; General Purpose; Handles; Hose; Overmolding; Profiles; Seals; Tubing; Weatherstripping; Wire & Cable

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density	1.19	g/cm ³	ISO 2781
Density - Specific Gravity	1.19	g/cm ³	ASTM D471
Change in Volume			
(in Reference Fuel B, 27 °C, 168 hr)	30	%	ASTM D471
(in Reference Fuel B, 27 °C, 168 hr)	30	%	ISO 1817
(in ASTM #1 Oil, 100 °C, 168 hr)	-10	%	ISO 1817
(in ASTM #1 Oil, 100 °C, 168 hr)	-10	%	ASTM D471
(in IRM 903 Oil, 100 °C, 168 hr)	27	%	ASTM D471
(in IRM 903 Oil, 100 °C, 168 hr)	27	%	ISO 1817
(in Water, 100 °C, 168 hr)	12	%	ASTM D471
(in Water, 100 °C, 168 hr)	12	%	ISO 1817
Melt Viscosity, (190 °C, 300 sec ⁻¹)	545	Pa·s	ASTM D3835
Mechanical			
Tensile Stress at 100%			
(1.90 mm)	3.90	MPa	ISO 37
(1.90 mm)	3.90	MPa	ASTM D412
(125 °C, 1.90 mm)	3.90	MPa	ISO 188
(125 °C, 1.90 mm)	3.90	MPa	ASTM D573

Torsion Modulus			
(24 °C, 1.9 mm)	1.9	MPa	ASTM D1043
Compression Molded			
(-20 °C, 1.9 mm)	7.5	MPa	ASTM D1043
Compression Molded			
Tensile Set	8	%	ASTM D412
Clash-Berg Modulus, (-38 °C)	68.9	MPa	ASTM D1043
Tensile Strength at Yield			
(1.90 mm)	9.60	MPa	ASTM D412
(125 °C, 1.90 mm)	10.6	MPa	ASTM D573
Tensile Stress at Yield			
(1.90 mm)	9.60	MPa	ISO 37
(125 °C, 1.90 mm)	10.6	MPa	ISO 188
Tensile Strain at Break			
(1.90 mm)	300	%	ISO 37
(125 °C, 1.90 mm)	330	%	ISO 188
Tensile Elongation at Break			
(125 °C, 1.90 mm)	330	%	ASTM D573
(1.90 mm)	300	%	ASTM D412
Tear Strength, (Die C, 1.90 mm)	26.3	kN/m	ASTM D624
Impact			
Ductile/Brittle Transition Temperature	-51	°C	ASTM D746
Hardness			
Change in Shore Hardness in Air, (Shore A, 125 °C, 168 hr)	5.0		ISO 188
Shore Hardness, (Shore A, 1.90 mm, Compression Molded)	62		ISO 868
Change in Durometer Hardness in Air, (Shore A, 125 °C, 168 hr)	5.0		ASTM D573
Durometer Hardness, (Shore A, 1.90 mm, Compression Molded)	62		ASTM D2240
Additional Information			
Compression Set			
(24 °C, 22 hr, Method B)	15	%	ASTM D395
(100 °C, 22 hr, Method B)	55	%	ASTM D395
(24 °C, 22 hr)	15	%	ISO 815
(100 °C, 22 hr)	55	%	ISO 815
Taber Abrasion Resistance, (CS-17 Wheel, 1000 g, 1000 Cycles)	7.00	mg	ASTM D1044

Injection Parameters		Nominal Value	Units
Processing (Melt) Temp		177	°C