

## Technical Data Sheet

### *Alcryn* 2095BKBLK



Melt Processable Rubber

#### Product Description

*Alcryn* 2095BKBLK is a Melt Processable Rubber material and is typically used in Blow Molding, Compression Molding, Extrusion, Injection Molding applications. Features include: Good Weather Resistance, High Flow, High Heat Resistance, Noise Damping, Oil Resistant, Ozone Resistant, UV Resistant, and Vibration Damping.

<b>Processing Method</b>	Blow Molding; Compression Molding; Extrusion; Injection Molding
<b>Attribute</b>	Good Weather Resistance; High Flow; High Heat Resistance; Noise Damping; Oil Resistant; Ozone Resistant; UV Resistant; Vibration Damping
<b>Forms</b>	Pellets
<b>Appearance</b>	Black
<b>Additive</b>	UV Stabilizer
<b>Application</b>	Cable Jacketing; Engineering Parts; Fabrics; Gaskets; Handles; Hose; Seals; Sheet; Tubing; Weatherstripping; Wire Jacketing

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Density	1.17	g/cm <sup>3</sup>	ISO 1183
Density - Specific Gravity	1.17	g/cm <sup>3</sup>	ASTM D792
Change in Volume			
(in ASTM #1 Oil, 100 °C, 168 hr)	-10	%	ASTM D471
(in Reference Fuel B, 24 °C, 168 hr)	43	%	ASTM D471
(in ASTM #3 Oil, 100 °C, 168 hr)	31	%	ASTM D471
<b>Mechanical</b>			
Tensile Set	24	%	ASTM D412
Tensile Strength at Yield, (1.91 mm, Compression Molded)	13.1	MPa	ASTM D638
Tensile Stress at Yield, (1.91 mm, Compression Molded)	13.1	MPa	ISO 527-2
Tensile Strain at Break, (1.91 mm, Compression Molded)	300	%	ISO 527-2
Tensile Elongation at Break, (1.91 mm, Compression Molded)	300	%	ASTM D638
Tensile Modulus			
(1.91 mm, Compression Molded)	8.48	MPa	ASTM D638
(1.91 mm, Compression Molded)	8.48	MPa	ISO 527-1
Tear Strength, (24 °C, Die C)	62.2	kN/m	ASTM D624
<b>Hardness</b>			
Durometer Hardness, (Shore A, 1.91 mm, Compression Molded)	93		ASTM D2240
IRHD Hardness	93		ISO 48

Injection Parameters	Nominal Value	Units
Processing (Melt) Temp	177	°C