

Technical Data Sheet

Accutech NY0730G40L

Polyamide 6
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.45	1.45 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	667000 psi	4600 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	24700 psi	170 MPa	
Break	24700 psi	170 MPa	
Tensile Elongation			ASTM D638
Yield	5.0 %	5.0 %	
Break	7.0 %	7.0 %	
Flexural Modulus	1.64E+6 psi	11300 MPa	ASTM D790
Flexural Strength	38100 psi	263 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	3.3 ft·lb/in	180 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	109	109	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed	392 °F	200 °C	

Notes

These are typical property values not to be construed as specification limits.