

Technical Data Sheet

Schulamid 6 GF 30 4DD BLACK

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Product Description

30% glass fibre reinforced flame-retardant Polyamide 6 grade; halogen free; heat stabilized; very good surface appearance

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Flame Retardant • Halogen Free
UL File Number	• E86615-103366094
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6 GF30 FR(40)

Physical	Dry	Conditioned	Unit	Test Method
----------	-----	-------------	------	-------------

Density	1.43	--	g/cm ³	ISO 1183/A
Viscosity Number	145	--	cm ³ /g	ISO 307

Mechanical	Dry	Conditioned	Unit	Test Method
------------	-----	-------------	------	-------------

Tensile Modulus	1.74E+6 (12000)	943000 (6500)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	20300 (140)	13800 (95.0)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	6.0	%	ISO 527-2/1A/5

Impact	Dry	Conditioned	Unit	Test Method
--------	-----	-------------	------	-------------

Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	4.3 (9.0)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	5.7 (12)	7.6 (16)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	29 (60)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	33 (70)	33 (70)	ft·lb/in ² (kJ/m ²)	

Thermal	Dry	Conditioned	Unit	Test Method
---------	-----	-------------	------	-------------

Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	419 (215)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	399 (204)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	397 (203)	--	°F (°C)	ISO 306/B50
--	414 (212)	--	°F (°C)	ISO 306/A50
Ball Pressure Test (392°F (200°C))	Pass	--		IEC 60695-10-2

Technical Data Sheet

Schulamid 6 GF 30 4DD BLACK

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	> 1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	> 1.0E+10	ohms·m	IEC 62631-3-1
Electric Strength ¹				IEC 60243-1
73°F (23°C), 0.0394 In (1.00 Mm), In Oil	710 (28)	--	V/mil (kV/mm)	
Comparative Tracking Index	475	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				ISO 3795
0.0295 In (0.750 Mm), Self-extinguishing	0.0	--	in/min (mm/min)	
0.0591 In (1.50 Mm), Self-extinguishing	0.0	--	in/min (mm/min)	
0.118 In (3.00 Mm), Self-extinguishing	0.0	--	in/min (mm/min)	
Flammability Classification				IEC 60695-11-10, -20
0.030 In (0.75 Mm)	V-0	--		
0.06 In (1.5 Mm)	V-0	--		
0.12 In (3.0 Mm)	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.030 In (0.75 Mm)	1760 (960)	--	°F (°C)	
0.06 In (1.5 Mm)	1760 (960)	--	°F (°C)	
0.12 In (3.0 Mm)	1760 (960)	--	°F (°C)	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.030 In (0.75 Mm)	1380 (750)	--	°F (°C)	
0.06 In (1.5 Mm)	1380 (750)	--	°F (°C)	
0.12 In (3.0 Mm)	1380 (750)	--	°F (°C)	
Oxygen Index	32	--	%	ISO 4589-2

Technical Data Sheet

Schulamid 6 GF 30 4DD BLACK

Polyamide 6
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Hopper Temperature	158 °F	70 °C
Processing (Melt) Temp	464 to 500 °F	240 to 260 °C
Mold Temperature	140 to 194 °F	60 to 90 °C
Injection Rate	Moderate	Moderate
Screw Speed	< 709 in/min	< 18 m/min

Notes

¹ 2000 V/sec

Notes

These are typical property values not to be construed as specification limits.