

Technical Data Sheet

Schulamid 6 GF7 FR4 K1681 BLK968076



Polyamide 6

Product Description

7% glass fibre reinforced flame retardant PA-6 grade; incandescent wire test without flame; without PBDE; GWIT > 800°C

Processing Method	Injection Molding
Additive	Flame Retardant
Filler/Reinforcement	Glass Fiber, 7.0%
Resin ID	PA6 GF7 FR(17+30)

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density, (Method A)	1.32	g/cm ³	ISO 1183
Mechanical			
Tensile Strain at Break			
(Type 1A, 5 mm/min)	3.4	%	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	19	%	ISO 527-2
Tensile Stress at Break			
(Type 1A, 5 mm/min)	75.0	MPa	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	40.0	MPa	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	5000	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	2300	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	3.5	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	3.5	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	8.8	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	35	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	30	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	78	kJ/m ²	ISO 179
Hardness			
Ball Pressure Test, (200 °C)	Pass		IEC 60695-10-2
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	205	°C	ISO 306
(A (10N), 120 °C/h)	218	°C	ISO 306

Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	208	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	170	°C	ISO 75-2/A
RTI Elec			
(1.5 mm)	130	°C	UL 746B
(3.0 mm)	130	°C	UL 746B
(0.75 mm)	130	°C	UL 746B
(0.38 mm)	130	°C	UL 746B
RTI Imp			
(1.5 mm)	100	°C	UL 746B
(3.0 mm)	100	°C	UL 746B
(0.75 mm)	90.0	°C	UL 746B
(0.38 mm)	75.0	°C	UL 746B
RTI Str			
(1.5 mm)	120	°C	UL 746B
(3.0 mm)	120	°C	UL 746B
(0.75 mm)	110	°C	UL 746B
(0.38 mm)	100	°C	UL 746B
Electrical			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	275	V	IEC 60112
High Amp Arc Ignition			UL 746A
Surface Resistivity	>1.0E+15	ohm	IEC 60093
Flammable			
Hot-wire Ignition (HWI)			UL 746A
Glow Wire Flammability Index			
(0.75 mm)	850	°C	IEC 60695-2-12
(1.5 mm)	960	°C	IEC 60695-2-12
(0.38 mm)	850	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			
(0.75 mm)	825	°C	IEC 60695-2-13
(1.5 mm)	850	°C	IEC 60695-2-13
(0.38 mm)	825	°C	IEC 60695-2-13
Oxygen Index	23	%	ISO 4589-2
UL Information			
Flammability Classification			
(0.38 mm)	V-2		IEC 60695-11-10, -20
(1.5 mm)	V-2		IEC 60695-11-10, -20
(3.0 mm)	V-2		IEC 60695-11-10, -20

Injection Parameters		Nominal Value	Units
Drying Time	4.0 to 6.0	hr	
Drying Temperature	80	°C	
Suggested Max Moisture	0.1	%	
Screw Speed	<250	mm/sec	
Processing (Melt) Temp	240 to 260	°C	
Injection Rate	Slow-Moderate		
Back Pressure	20 to 80	bar	
Mold Temperature	60 to 90	°C	