

Technical Data Sheet

# Schulamid 6 MV HI

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics

## Product Description

Higher impact Polyamide 6 - standard grade

## General

Features	<ul style="list-style-type: none"><li>Grease Resistant</li><li>High Impact Resistance</li></ul>	<ul style="list-style-type: none"><li>Low Temperature Toughness</li><li>Medium Viscosity</li></ul>	<ul style="list-style-type: none"><li>Oil Resistant</li></ul>
Automotive Specifications	• GM QK 002621 P Color: Natural • IMDS ID 4221280 Color: Natural		
UL File Number	• E86615		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PA6-I		

Physical	Dry	Conditioned	Unit	Test Method
Density	1.11	--	g/cm <sup>3</sup>	ISO 1183/A
Water Absorption				ISO 62
Equilibrium, 73°F (23°C), 50% Rh	2.3	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	319000 (2200)	116000 (800)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Yield)	8700 (60.0)	5080 (35.0)	psi (MPa)	ISO 527-2/1A/50
Tensile Strain (Yield)	4.2	20	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	> 50	> 100	%	ISO 527-2/1A/50
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	4.8 (10)	--	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
73°F (23°C)	7.6 (16)	29 (60)	ft·lb/in <sup>2</sup> (kJ/m <sup>2</sup> )	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	No Break	--		
73°F (23°C)	No Break	No Break		
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 358/30)	16000 (110)	8700 (60.0)	psi (MPa)	ISO 2039-1
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	284 (140)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	140 (60.0)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	347 (175)	--	°F (°C)	ISO 306/B50
--	419 (215)	--	°F (°C)	ISO 306/A50

Technical Data Sheet

# Schulamid 6 MV HI


Polyamide 6  
LyondellBasell Industries  
Engineering Plastics

Thermal	Dry	Conditioned	Unit	Test Method
RTI Elec				UL 746B
0.06 In (1.5 Mm)	149 (65.0)	--	°F (°C)	
0.12 In (3.0 Mm)	149 (65.0)	--	°F (°C)	
RTI Imp				UL 746B
0.06 In (1.5 Mm)	149 (65.0)	--	°F (°C)	
0.12 In (3.0 Mm)	149 (65.0)	--	°F (°C)	
RTI Str				UL 746B
0.06 In (1.5 Mm)	149 (65.0)	--	°F (°C)	
0.12 In (3.0 Mm)	149 (65.0)	--	°F (°C)	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	> 1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	> 1.0E+10	ohms·m	IEC 62631-3-1
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 In (2.00 Mm)	< 3.9 (< 100)	--	in/min (mm/min)	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 (< 100)	--	in/min (mm/min)	FMVSS 302
Flammability Classification				IEC 60695-11-10, -20
0.030 In (0.75 Mm)	HB	--		
0.06 In (1.5 Mm)	HB	--		
0.12 In (3.0 Mm)	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.06 In (1.5 Mm)	1200 (650)	--	°F (°C)	
0.12 In (3.0 Mm)	1200 (650)	--	°F (°C)	

Technical Data Sheet

# Schulamid 6 MV HI

Polyamide 6  
LyondellBasell Industries  
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	482 to 518 °F	250 to 270 °C
Mold Temperature	140 to 194 °F	60 to 90 °C

## Notes

These are typical property values not to be construed as specification limits.