

Technical Data Sheet

Schulamid 6 GF15 FR4 K1681 NAT



Polyamide 6

Product Description

15% glass fibre reinforced flame-retardant Polyamide 6 grade without PBDE.

CAE data for rheological simulation available on request.

Processing Method Injection Molding

Filler/Reinforcement Glass Fiber, 15%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density, (Method A)	1.38	g/cm ³	ISO 1183
Viscosity Number	136	cm ³ /g	ISO 307
Mechanical			
Tensile Strain at Break, (Type 1A, 23 °C, 5 mm/min)	2.7	%	ISO 527-2
Tensile Stress at Break, (Type 1A, 23 °C, 5 mm/min)	113	MPa	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	6900	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	7.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched, (23 °C, Type 1, Edgewise)	43	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	205	°C	ISO 306
(A (10N), 50 °C/h)	212	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	216	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	200	°C	ISO 75-2/A
Electrical			
Volume Resistivity	1000000000 0000	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	250	V	IEC 60112
Surface Resistivity	1E+15	ohm	IEC 60093
Flammable			

Glow Wire Flammability Index			
(0.75 mm)	960	°C	IEC 60695-2-12
(1.5 mm)	960	°C	IEC 60695-2-12
(3.0 mm)	960	°C	IEC 60695-2-12
(0.38 mm)	800	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			
(0.75 mm)	900	°C	IEC 60695-2-13
(1.5 mm)	900	°C	IEC 60695-2-13
(3.0 mm)	900	°C	IEC 60695-2-13
(0.38 mm)	825	°C	IEC 60695-2-13
Oxygen Index	26	%	ISO 4589-2

UL Information

Flame Rating			
(1.6 mm)	V-2		UL 94
(3.2 mm)	V-2		UL 94
(0.8 mm)	V-2		UL 94
(0.40 mm)	V-2		UL 94
Flammability Classification			
(0.40 mm)	V-2		IEC 60695-11-10, -20
(0.8 mm)	V-2		IEC 60695-11-10, -20
(1.6 mm)	V-2		IEC 60695-11-10, -20
(3.2 mm)	V-2		IEC 60695-11-10, -20
UL File Number	E86615		

Injection Parameters		Nominal Value	Units
Drying Time		4.0 to 6.0	hr
Drying Temperature		80	°C
Suggested Max Moisture		0.1	%
Screw Speed		<250	mm/sec
Processing (Melt) Temp		240 to 260	°C
Injection Rate		Slow-Moderate	
Back Pressure		20 to 80	bar
Mold Temperature		60 to 90	°C