

Technical Data Sheet

Schulamid 6 MV HI K1207 BLK 968001



Polyamide 6

Product Description

PA 6, impact modified

Processing Method Injection Molding

Attribute Impact Modified

Additive Impact Modifier

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density, (Method A)	1.05	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	45.0	MPa	ISO 527-2
Tensile Strain at Yield, (Type 1A, 50 mm/min)	4.0	%	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	1700	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	61	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched, (23 °C, Type 1, Edgewise)	No Break		ISO 179
Thermal			
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	170	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	69.0	°C	ISO 75-2/A
Electrical			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
- Conditioned	10000000000 0	ohm*m	IEC 62631-3-1
Surface Resistivity	>1.0E+15	ohm	IEC 60093
Flammable			
Burning Rate			
(2.00 mm)	<100	mm/min	ISO 3795
(2.00 mm)	<100	mm/min	FMVSS 302

Injection Parameters	Nominal Value	Units
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Suggested Max Moisture	0.040 to 0.10	%
Processing (Melt) Temp	250 to 270	°C
Mold Temperature	60 to 90	°C