

Technical Data Sheet

Schulamid 6 RBL3000 BLK



Polyamide 6

Product Description

30% glass fiber reinforced PA 6, Recycled Grade

Processing Method Injection Molding

Filler/Reinforcement Glass Fiber, 30%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density, (Method A)	1.35	g/cm ³	ISO 1183
Viscosity Number	139	cm ³ /g	ISO 307
Mechanical			
Tensile Strain at Break			
(Type 1A, 5 mm/min)	2.5	%	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	6.7	%	ISO 527-2
Tensile Stress at Break			
(Type 1A, 5 mm/min)	160	MPa	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	95.0	MPa	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	9500	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	6200	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	9.0	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	7.0	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	15	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	55	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	48	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	70	kJ/m ²	ISO 179
Thermal			
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	218	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	202	°C	ISO 75-2/A
Flammable			
Burning Rate			
(2.00 mm)	<100	mm/min	FMVSS 302
(2.00 mm)	<100	mm/min	ISO 3795

Injection Parameters	Nominal Value	Units
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Suggested Max Moisture	0.040 to 0.10	%
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	60 to 100	°C