

Technical Data Sheet

# Schulamid 612 CT GFS30

Polyamide 612  
LyondellBasell Industries  
Engineering Plastics

## Product Description

Schulamid® 612 CT GFS30 is a 612 polyamide with 30% fiber reinforcement. Schulamid® 612 CT GFS30 is an injection molding grade product for connectors.

## General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Chemical Resistant
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.25 g/cm <sup>3</sup>	1.25 g/cm <sup>3</sup>	ASTM D1505
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Break)	16500 psi	114 MPa	ISO 527-2
Tensile Strain (Break)	5.0 %	5.0 %	ISO 527-2
Flexural Modulus	1.19E+6 psi	8170 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	9.0 ft·lb/in <sup>2</sup>	19 kJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value (English)	Nominal Value (SI)	
Melting Temperature	419 °F	215 °C	

## Notes

These are typical property values not to be construed as specification limits.