

Technical Data Sheet

Schulamid 612 FS 5104

Polyamide 612
LyondellBasell Industries
Engineering Plastics

Product Description

Impact modified Polyamide 612 with electrical neutral heat stabilization system for extrusion applications. Heat stabilization system with very low halogen content (<30 ppm).

General

Features	<ul style="list-style-type: none"> • Chemical Resistant • Corrosion Resistant • Fuel Resistant • Good Dimensional Stability 	<ul style="list-style-type: none"> • Heat Aging Resistant • High Impact Resistance • Low Temperature Toughness • Low to No Water Absorption 	<ul style="list-style-type: none"> • Medium-high Viscosity • Oil Resistant
Processing Method	<ul style="list-style-type: none"> • Extrusion 		

Physical	Dry	Conditioned	Unit	Test Method
----------	-----	-------------	------	-------------

Density	1.01	--	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (275°C/10.0 Kg)	12	--	cm ³ /10min	ISO 1133

Mechanical	Dry	Conditioned	Unit	Test Method
------------	-----	-------------	------	-------------

Tensile Modulus	160000 (1100)	66700 (460)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	5370 (37.0)	5510 (38.0)	psi (MPa)	ISO 527-2/1A/50
Nominal Tensile Strain at Break	> 200	> 270	%	ISO 527-2/1A/50
Flexural Modulus	142000 (980)	--	psi (MPa)	ISO 178

Impact	Dry	Conditioned	Unit	Test Method
--------	-----	-------------	------	-------------

Charpy Notched Impact Strength				ISO 179/1eA
-40°F (-40°C)	29 (61)	--	ft-lb/in ² (kJ/m ²)	
73°F (23°C)	47 (98)	50 (110)	ft-lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-40°F (-40°C)	No Break	--		
73°F (23°C)	No Break	No Break		

Hardness	Dry	Conditioned	Unit	Test Method
----------	-----	-------------	------	-------------

Ball Indentation Hardness (H 132/30)	8560 (59.0)	--	psi (MPa)	ISO 2039-1
--------------------------------------	----------------	----	--------------	------------

Thermal	Dry	Conditioned	Unit	Test Method
---------	-----	-------------	------	-------------

Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	158 (70.0)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	102 (39.0)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	189 (87.0)	--	°F (°C)	ISO 306/B50
--	392 (200)	--	°F (°C)	ISO 306/A50

Technical Data Sheet

Schulamid 612 FS 5104


Polyamide 612
LyondellBasell Industries
Engineering Plastics

Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 In (2.00 Mm)	< 3.9 (< 100)	--	in/min (mm/min)	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 (< 100)	--	in/min (mm/min)	FMVSS 302
Flammability Classification				IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	--		
0.12 In (3.0 Mm)	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.06 In (1.5 Mm)	1250 (675)	--	°F (°C)	
0.12 In (3.0 Mm)	1250 (675)	--	°F (°C)	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.06 In (1.5 Mm)	1200 (650)	--	°F (°C)	
0.12 In (3.0 Mm)	1200 (650)	--	°F (°C)	

Technical Data Sheet

Schulamid 612 FS 5104

Polyamide 612
LyondellBasell Industries
Engineering Plastics



Extrusion	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Melt Temperature	446 to 518 °F	230 to 270 °C

Notes

These are typical property values not to be construed as specification limits.