

Technical Data Sheet

Lucent Pa 66-41

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description

Unreinforced Nylon 66, Toughened

Colors Available

Add "H" for Heat Stabilized

Add "HU" for Weatherable

Typical Properties, Dry as Molded

General

Appearance

- Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.09	1.09 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	8400 psi	57.9 MPa	ASTM D638
Tensile Elongation (Break)	> 30 %	> 30 %	ASTM D638
Flexural Modulus	290000 psi	2000 MPa	ASTM D790
Flexural Strength	9500 psi	65.5 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	3.0 ft·lb/in	160 J/m	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed	162 °F	72.2 °C	
Peak Melting Temperature	482 to 509 °F	250 to 265 °C	ASTM D789

Notes

These are typical property values not to be construed as specification limits.