

Technical Data Sheet

Lucent Pa NP6-140

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description

15% Glass/25% Mineral Reinforced Nylon 6

Colors Available
Add "H" for Heat Stabilized
Add "HU" for Weatherable
Typical Properties, Dry as Molded
Meets GMP.PA6.013

General

Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight • Mineral, 25% Filler by Weight
Appearance	• Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.48	1.48 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	14500 psi	100 MPa	ASTM D638
Tensile Elongation (Break)	1.0 %	1.0 %	ASTM D638
Flexural Modulus	900000 psi	6210 MPa	ASTM D790
Flexural Strength	22000 psi	152 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	0.80 ft·lb/in	43 J/m	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed	382 °F	194 °C	
Peak Melting Temperature	420 to 437 °F	216 to 225 °C	ASTM D789

Notes

These are typical property values not to be construed as specification limits.