

Technical Data Sheet

Matrixx F663E13


Polyamide 66
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 13% Filler by Weight		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.22	1.22 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	16500 psi	114 MPa	ASTM D638
Flexural Modulus - Tangent	720000 psi	4960 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	1.0 ft·lb/in	53 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	460 °F	238 °C	ASTM D648
RTI Str	150 °F	65.6 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94

Technical Data Sheet

Matrixx F663E13

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 200 °F	71 to 93 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	520 to 570 °F	271 to 299 °C
Middle Temperature	520 to 570 °F	271 to 299 °C
Front Temperature	520 to 570 °F	271 to 299 °C
Processing (Melt) Temp	530 to 570 °F	277 to 299 °C
Mold Temperature	150 to 200 °F	66 to 93 °C
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	< 50.0 psi	< 0.345 MPa
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes

Screw Speed: Slow to Medium
Dessicant dryer with -20°F dewpoint

Notes

These are typical property values not to be construed as specification limits.