

## Technical Data Sheet

### *Icorene* N9302-1200 NAT 0000



Polybutylene Terephthalate

#### Product Description

*Icorene* N9302 is based on a high flow grade PBT designed for injection moulding and extrusion. *Icorene* N9302 is available as a powder suitable for use in making masterbatch or compounds. *Icorene* N9302 is not intended for use in medical or pharmaceutical applications.

Forms Powder

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Volume Flow Rate, (250 °C/2.16 kg)	45	cm <sup>3</sup> /10 min	ISO 1133
Density	1.30	g/cm <sup>3</sup>	ISO 1183
<b>Thermal</b>			
Melting Temperature	225	°C	DSC