

Technical Data Sheet

# Matrixx 34S5201

Polybutylene Terephthalate  
LyondellBasell Industries  
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Additive	• Flame Retardant		
Features	• Flame Retardant		
Physical			
Density / Specific Gravity	Nominal Value (English)	Nominal Value (SI)	Test Method
	1.56	1.56 g/cm <sup>3</sup>	ASTM D792
Mechanical			
Tensile Strength	Nominal Value (English)	Nominal Value (SI)	Test Method
Yield, 73°F (23°C), 0.125 In (3.18 Mm)	16000 psi	110 MPa	ASTM D638
Flexural Modulus - Tangent			ASTM D790
73°F (23°C), 0.125 In (3.18 Mm)	840000 psi	5790 MPa	
Impact			
Notched Izod Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
73°F (23°C), 0.125 In (3.18 Mm)	1.0 ft·lb/in	53 J/m	ASTM D256
Thermal			
Deflection Temperature Under Load	Nominal Value (English)	Nominal Value (SI)	Test Method
66 Psi (0.45 Mpa), Unannealed, 0.125 In (3.18 Mm)	421 °F	216 °C	ASTM D648
264 Psi (1.8 Mpa), Unannealed, 0.125 In (3.18 Mm)	405 °F	207 °C	
RTI Elec	167 °F	75.0 °C	UL 746B
RTI Imp	167 °F	75.0 °C	UL 746B
RTI Str	167 °F	75.0 °C	UL 746B
Flammability			
Flame Rating (0.06 In (1.5 Mm))	Nominal Value (English)	Nominal Value (SI)	Test Method
	V-0	V-0	UL 94
Additional Information			
Reinforcement Content	Nominal Value (English)	Nominal Value (SI)	Test Method
	20 %	20 %	ASTM D5630

## Notes

These are typical property values not to be construed as specification limits.