

Technical Data Sheet

# Schuladur A GF 20

Polybutylene Terephthalate  
LyondellBasell Industries  
Engineering Plastics

## Product Description

20% glass fibre reinforced PBT compound

## General

Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Automotive Specifications	• GM QK 006613 Color: 968001 Black
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PBT-GF

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.45 g/cm <sup>3</sup>	1.45 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (250°C/2.16 Kg)	20 cm <sup>3</sup> /10min	20 cm <sup>3</sup> /10min	ISO 1133
Water Absorption			ISO 62
Equilibrium, 73°F (23°C), 50% Rh	0.30 %	0.30 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.02E+6 psi	7000 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	16700 psi	115 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.5 %	2.5 %	ISO 527-2/1A/5
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	3.8 ft·lb/in <sup>2</sup>	8.0 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	27 ft·lb/in <sup>2</sup>	57 kJ/m <sup>2</sup>	ISO 179/1eU
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 961/30)	29700 psi	205 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	419 °F	215 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	383 °F	195 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	406 °F	208 °C	ISO 306/B50
--	424 °F	218 °C	ISO 306/A50
Ball Pressure Test (392°F (200°C))	Pass	Pass	IEC 60695-10-2
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	400 V	400 V	IEC 60112
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	1.6 in/min	40 mm/min	ISO 3795
0.0787 In (2.00 Mm)	1.6 in/min	40 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1200 °F	650 °C	
0.12 In (3.0 Mm)	1200 °F	650 °C	

Technical Data Sheet

**Schuladur A GF 20**

Polybutylene Terephthalate  
LyondellBasell Industries  
Engineering Plastics

**Additional Information**

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

# Schuladur A GF 20

Polybutylene Terephthalate  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	248 °F	120 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.05 %	0.05 %
Processing (Melt) Temp	482 to 500 °F	250 to 260 °C
Mold Temperature	158 to 194 °F	70 to 90 °C

### Notes

These are typical property values not to be construed as specification limits.