

Technical Data Sheet

Schuladur A GF 30 FR 1 BLK968093



Polybutylene Terephthalate

Product Description

Flame retardant PBT with 30% glass fibre and halogenous flame retardant agent; without PBDE

Processing Method	Injection Molding
Attribute	Halogenated
Additive	Flame Retardant
Filler/Reinforcement	Glass Fiber, 30%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (260 °C/5.0 kg)	10	cm ³ /10 min	ISO 1133
Density, (Method A)	1.64	g/cm ³	ISO 1183
Mechanical			
Tensile Strain at Break, (Type 1A, 5 mm/min)	2.5	%	ISO 527-2
Tensile Stress at Break, (Type 1A, 5 mm/min)	132	MPa	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	11000	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	11	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	9.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	62	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	60	kJ/m ²	ISO 179
Thermal			
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	220	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	204	°C	ISO 75-2/A
Electrical			
Volume Resistivity	>1.0E+13	ohm*cm	IEC 60093
Comparative Tracking Index (CTI)	150	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093
Flammable			
Glow Wire Flammability Index			
(0.75 mm)	960	°C	IEC 60695-2-12
(1.5 mm)	960	°C	IEC 60695-2-12
(3.0 mm)	960	°C	IEC 60695-2-12

Glow Wire Ignition Temperature			
(0.75 mm)	675 °C		IEC 60695-2-13
(1.5 mm)	650 °C		IEC 60695-2-13
(3.0 mm)	725 °C		IEC 60695-2-13
Oxygen Index	32 %		ISO 4589-2

UL Information

Flammability Classification			
(0.75 mm)	V-0		IEC 60695-11-10, -20
(1.5 mm)	V-0		IEC 60695-11-10, -20
(1.5 mm)	5VA		IEC 60695-11-10, -20